



Technical Data Sheet

ETAP WHITE TOP KRAFT LINER (W-KLB)

Test	Test Method	Unit	Tolerance	Target			
				135	140	150	200
Grammage	Tappi-410	g/m ²	(± 3%)	135	140	150	200
Burst	Tappi-807	kpa	(± 5%)	495	515	550	700
Thickness	Tappi-411	micron	(± 10%)	200	205	220	290
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	2.9	3.0	3.2	4.1
Brightness	ISO 2470	%	(+ 3%)	80	80.0	80	80.0
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	215	220	240	300
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	95	100	110	140
COBB 60 (Top)	Tappi-441	g/m ²	max=40	25	25	25	25
COBB 60 (Bottom)	Tappi-441	g/m ²	max=120	30	30	30	30
Gurley Porosity	Tappi-460	Sec/100 ml		30	30	30	40
Internal Bond strength (Scott)	Tappi-569	J/m ²	min=120	200	200	200	200
Moisture Content	Tappi-412	%	(± 1%)	8	8	8	8

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Made From 100% Virgin Pulp

Excellent runnability and properties.

ISO 9001 , 14001 , 45001 Certified Company