



Technical Data Sheet

ETAP TESTLINER 2 (TL2)

Test	Test Method	Unit	Tolerance	Target									
				110	120	125	130	135	140	150	160	175	200
Grammage	Tappi-410	g/m ²	(± 3%)	110	120	125	130	135	140	150	160	175	200
Burst	Tappi-807	kpa	(± 5%)	255	280	290	310	315	320	350	370	400	460
Thickness	Tappi-411	micron	(± 10%)	165	180	180	185	200	205	220	225	230	250
R.C.T (CD)	Tappi-822	Kgf	(± 5%)	13.5	14.5	15	16	16.5	16.7	18	19	21	24
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	2	2.1	2.2	2.3	2.35	2.35	2.4	2.55	2.8	3.2
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	145	160	165	170	175	180	190	200	220	250
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	55	60	65	70	75	80	85	90	100	110
COBB 60 (Top)	Tappi-441	g/m ²	max=40	30	30	30	30	30	30	30	30	30	30
COBB 60 (Bottom)	Tappi-441	g/m ²	max=120	40	40	40	40	40	40	40	40	40	40
Gurley Porosity	Tappi-460	Sec/100 ml		30	30	30	30	35	35	35	35	35	40
Moisture Content	Tappi-412	%	(± 1%)	8	8	8	8	8	8	8	8	8	8

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Made from 100% recycled fibers

Excellent runnability and properties

ISO 9001 , 14001 , 45001 Certified Company

FSC License : FSC - C154518