



Technical Data Sheet

ETAP KRAFT TOP LINER (BKTL)

Test	Test Method	Unit	Tolerance	Target					
				125	130	135	140	150	200
Grammage	Tappi-410	g/m ²	(± 3%)	125	130	135	140	150	200
Burst	Tappi-807	kpa	(± 5%)	415	4.35	450	465	500	630
Thickness	Tappi-411	micron	(± 10%)	19	195	200	205	220	280
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	2.5	2.6	2.7	2.8	3	3.8
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	187	195	205	215	230	300
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	100	105	110	112	120	150
COBB 60 (Top)	Tappi-441	g/m ²	max=40	29	29	29	29	29	29
COBB 60 (Bottom)	Tappi-441	g/m ²	max=120	33	33	33	33	33	33
Gurley Porosity	Tappi-460	Sec/100 ml		25	25	30	30	30	35
Moisture Content	Tappi-412	%	(± 1%)	8	8	8	8	8	8

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Top Ply Made From 100% Virgin Pulp

Excellent runnability and properties.

ISO 9001 , 14001 , 45001 Certified Company