



Technical Data Sheet

ETAP HP FLUTE 2

Test	Test Method	Unit	Tolerance	Target					
				120	125	130	140	150	170
Grammage	Tappi-410	g/m ²	(± 3%)	247	258	268	290	310	350
Burst	Tappi-807	kpa	(± 5%)	182	195	195	200	220	225
Thickness	Tappi-411	micron	(± 10%)	2.2	2.3	2.4	2.55	2.75	3.1
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	210	215	225	240	260	290
C.M.T 30 (MD)	Tappi-809	N	(± 5%)	240	250	260	280	300	340
C.C.T (CD)	Tappi-843	N	(± 5%)	145	150	155	170	180	205
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	55	58	60	65	70	80
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	8	8	8	8	8	8
Water Absorption	Tappi-831	Second	(+ 1%)	8	8	8	8	8	8
Moisture Content	Tappi-412	%	(± 1%)	8	8	8	8	8	8

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Made from 100% recycled fibers

Excellent runnability and properties

ISO 9001 , 14001 , 45001 Certified Company

FSC License : FSC - C154518