



Technical Data Sheet

ETAP KRAFT LINER (KLB)

Test	Test Method	Unit	Tolerance	Target					
				130	135	140	150	185	200
Grammage	Tappi-410	g/m ²	(± 3%)	130	135	140	150	185	200
Burst	Tappi-807	kpa	(± 5%)	555	575	600	640	690	750
Thickness	Tappi-411	micron	(± 10%)	195	200	205	220	265	290
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	2.8	2.9	3.0	3.2	3.7	4.0
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	230	235	245	260	290	320
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	105	110	115	120	145	160
COBB 60 (Top)	Tappi-441	g/m ²	max=40	20	20	20	20	20	20
COBB 60 (Bottom)	Tappi-441	g/m ²	max=120	25	25	25	25	25	25
Gurley Porosity	Tappi-460	Sec/100 ml		20	20	20	25	27	30
Moisture Content	Tappi-412	%	(± 1%)	8	8	8	8	8	8

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Made From Virgin Pulp

Excellent runnability and properties.

ISO 9001 , 14001 , 45001 Certified Company