



Technical Data Sheet

ETAP WHITE TOP TEST LINER 2 (WTTL2)

Test	Test Method	Unit	Tolerance	Target		
Grammage	Tappi-410	g/m ²	(± 3%)	125	130	140
Burst	Tappi-807	kpa	(± 5%)	295	305	330
Thickness	Tappi-411	micron	(± 10%)	200	210	220
Brightness	ISO 2470	%	(+ 3%)	75	75	75
R.C.T (CD)	Tappi-822	Kgf	(± 5%)	15	15.5	17
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	2.05	2.1	2.3
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	160	165	180
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	76	79	85
COBB 60 (Top)	Tappi-441	g/m ²	max=40	30	30	30
COBB 60 (Bottom)	Tappi-441	g/m ²	max=120	40	40	40
Gurley Porosity	Tappi-460	Sec/100 ml		40	40	40
Internal Bond strength (Scott)	Tappi-569	J/m ²	min=120	200	200	200
Moisture Content	Tappi-412	%	(± 1%)	8	8	8

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Made from 100% of high quality recycled fibers.

Excellent runnability and properties.

ISO 9001 , 14001 , 45001 Certified Company

FSC License : FSC - C154518