



Etap co. For Paper & Board
Quality Assurance Dept.

Test Liner 150 Gsm (TL 3)

| Test Type | Test Method | Unit | Target | Tolerance |
|------------------|-------------|------------------|--------|-----------|
| Grammage | T-410 | g/m ² | 150 | 3% |
| Thickness | T-411 | mm | 0.22 | 5% |
| R.C.T | T-822 | Kg.f | 14/21 | 5% |
| Burst | T-807 | bar | 3 | 5% |
| S.C.T(CD) | T-826 | KN/m | 2.1 | 5% |
| Tensile Strength | T-494 | Kg.f | 17/7 | 5% |
| Water Absorption | | Sec | 2 | |
| Moisture Content | T-412 | % | 7-8 | |

Comment: All Tests are Done at 23° C and 50% RH.