



TESTLINER 1 (TL1)

Test	Test Method	Unit	Tolerance	Target						
				125	135	140	150	175	200	240
Grammage	T-410	g/m ²	3%	125	135	140	150	175	200	240
Burst	T-807	Bar	±5%	3.5	3.6	3.8	4	4.4	5	5.8
Thickness	T-411	micron		180	200	210	220	250	280	330
R.C.T (MD)	T-822	Kgf	±5%	17	19	20	21	23	26	30
R.C.T (CD)	T-822	Kgf	±5%	23	25	26	28	32	37	44
S.C.T (CD)	T-826	KN/m	±5%	2.4	2.5	2.6	2.8	3.1	3.4	4
Tensile Strength (MD)	T-494	Kgf	±5%	17	18	19	20	23	26	30
Tensile Strength (CD)	T-494	Kgf	±5%	8	8.5	9	10	12	14	16
C.O.B.B (top)	T-441	g/m ²	±5%	29	29	29	29	29	29	29
C.O.B.B (Bottom)	T-441	g/m ²		40	40	40	40	40	40	40
Moisture Content	T-412	%	±1	7	7	7	7	7	7	7

All tests are done at 23°C and 50% RH.

Reel width : 500-2500mm

Reel diameter: 1300mm

Core diameter: 75-100mm

