



## Technical Data Sheet

# ETAP TESTLINER 2 (TL2)

Test	Test Method	Unit	Tolerance	Target						
				120	125	130	140	150	175	200
Grammage	Tappi-410	g/m <sup>2</sup>	( ± 3% )	120	125	130	140	150	175	200
Burst	Tappi-807	kpa	( ± 5% )	280	290	310	320	350	400	460
Thickness	Tappi-411	micron	( ± 10% )	180	180	185	205	220	230	250
R.C.T ( MD )	Tappi-822	Kgf	( ± 5% )	14.5	15	16	16.7	18	21	24
R.C.T ( CD )	Tappi-822	Kgf	( ± 5% )	20	21	21.5	22.4	24	28	32
S.C.T ( CD )	Tappi-826	kN/m	( ± 5% )	2.2	2.2	2.3	2.3	2.4	2.8	3.2
Tensile Strength ( MD )	Tappi-494	N/2.5 cm	( ± 5% )	160	165	170	180	190	220	250
Tensile Strength ( CD )	Tappi-494	N/2.5 cm	( ± 5% )	60	65	70	80	85	100	110
COBB 60 ( Top )	Tappi-441	g/m <sup>2</sup>	max=40	30	30	30	30	30	30	30
COBB 60 ( Bottom )	Tappi-441	g/m <sup>2</sup>	max=120	40	40	40	40	40	40	40
Moisture Content	Tappi-412	%	( ± 1% )	8	8	8	8	8	8	8

All tests were done at 23<sup>0</sup> C and 50 % RH.

Reel width : 500-2500 mm

Reel diameter : 1300 mm

Core diameter : 75-100 mm

Made from 100% recycled fibers

Excellent runnability and properties

**ISO 9001 , 14001 , 45001 Certified Company**

**FSC License : FSC - C154518**