



Technical Data Sheet

ETAP SEMICHEMICAL FLUTE 2

Test	Test Method	Unit	Tolerance	Target
Grammage	Tappi-410	g/m ²	(± 3%)	150
Burst	Tappi-807	kpa	(± 5%)	380
Thickness	Tappi-411	micron	(± 10%)	220
S.C.T (CD)	Tappi-826	kN/m	(± 5%)	3.4
C.M.T 30 (MD)	Tappi-809	N	(± 5%)	350
C.C.T 30 (CD)	Tappi-843	N	(± 5%)	400
Tensile Strength (MD)	Tappi-494	N/2.5 cm	(± 5%)	220
Tensile Strength (CD)	Tappi-494	N/2.5 cm	(± 5%)	105
COBB 60 (Top)	Tappi-441	g/m ²	max=40	25
COBB 60 (Bottom)	Tappi-441	g/m ²	max=120	25
Moisture Content	Tappi-412	%	(± 1%)	7

All tests were done at 23⁰ C and 50 % RH.

Reel width : 500-2500 mm
 Reel diameter : 1300 mm
 Core diameter : 75-100 mm

Made from 100% of high quality recycled fibers.
 Excellent runnability and properties

ISO 9001 , 14001 , 45001 Certified Company
FSC License : FSC - C154518