



ETAP LINER

TestLiner TL1

Tec
cal
Dat
n

Test	Test Method	unit	Tolerance	Target						
grammage	T-410	g/m ²	3%	125	135	140	150	175	200	240
Burst	T-807	Bar	±5%	3.15	3.4	3.55	3.8	4.4	5	6
Thickness	T-411	micron		180	200	210	220	250	280	330
R.C.T (MD)	T-822	Kgf	±5%	17	18	19	20	23	26	32
R.C.T (CD)	T-822	Kgf	±5%	23	25	26	28	32	37	44
S.C.T (CD)	T-826	KN/m	±5%	2.3	2.4	2.5	2.7	3.1	3.5	4
Tensile Strength (MD)	T-494	Kgf	±5%	17	18	19	20	23	26	30
Tensile Strength (CD)	T-494	Kgf	±5%	8	8.5	9	10	11	12.5	14
C.O.B.B (top)	T-441	g/m ²		29	29	29	29	29	29	29
C.O.B.B (Bottom)	T-441	g/m ²		40	40	40	40	40	40	40
Moisture Content	T-412	%	±1	7	7	7	7	7	7	7

Comment: All Tests are Done at 23° C and 50% RH.

Reel Width	50-250 Cm
Reel Diameter	130 Cm
Core Diameter	75-100 Mm