



ETAP Top KRAFT Top KraftLiner

Test	Test Method	unit	Tolerance	140	150	200
grammage	T-410	g/m ²	3%	140	150	200
Burst	T-807	Bar	±5%	4.4	4.7	5.8
Thickness	T-411	micron		210	220	280
R.C.T (MD)	T-822	Kgf	±5%	24	26	34
R.C.T (CD)	T-822	Kgf	±5%	32	34	45
S.C.T (CD)	T-826	KN/m	±5%	2.8	3	4
Tensile Strength (MD)	T-494	Kgf	±5%	22	23	29
Tensile Strength (CD)	T-494	Kgf	±5%	10	11	14
C.O.B.B (top)	T-441	g/m ²	±5%	29	29	29
C.O.B.B (Bottom)	T-441	g/m ²		33	33	33
Moisture Content	T-412	%	±1	7	7	7

Comment: All Tests are Done at 23° C and 50% RH.

Reel Width	50-250 Cm
Reel Diameter	130 Cm
Core Diameter	75-100 Mm