



# Top-Kraft

Test	Test Method	Unit	Tolerance	Target		
Grammage	T-410	g/m <sup>2</sup>	3%	140	150	200
Burst	T-807	Bar	±5%	4.4	4.7	6.1
Thickness	T-411	micron		210	220	280
R.C.T (MD)	T-822	Kgf	±5%	24	26	34
R.C.T (CD)	T-822	Kgf	±5%	32	34	42
S.C.T (CD)	T-826	KN/m	±5%	2.8	3.2	4
Tensile Strength (MD)	T-494	Kgf	±5%	22	23	30
Tensile Strength (CD)	T-494	Kgf	±5%	10	11.5	15
C.O.B.B (top)	T-441	g/m <sup>2</sup>	±5%	29	29	29
C.O.B.B (Bottom)	T-441	g/m <sup>2</sup>		33	33	33
Moisture Content	T-412	%	±1	7	7	7

All tests are done at 23°C and 50% RH.

Reel width : 500-2500mm

Reel diameter: 1300mm

Core diameter: 75-100mm

