



Etap co. For Paper & Board
Quality Assurance Dept.

Test Liner 150 Gsm (TL 2)

Test Type	Test Method	Unit	Target	Tolerance
Grammage	T-410	g/m ²	150	3%
Thickness	T-411	mm	0.22	5%
R.C.T	T-822	Kg.f	18/24	5%
Burst	T-807	bar	3.5	5%
S.C.T(CD)	T-826	KN/m	2.4	5%
Tensile Strength	T-494	Kg.f	19/8.5	5%
C.O.B.B (Top)		g/m ²	40	
Moisture Content	T-412	%	7-8	

Comment: All Tests are Done at 23° C and 50% RH.